UNOSHIELD



Ultra-Premium Quality Acrylic Putty

DESCRIPTION AND USES

- UNOSHIELD is ultra-premium quality heavy-duty putty based on acrylic copolymer.
- Although designed for exterior, it can also be used for tough interior conditions.
- Specially formulated to give excellent filling and sanding properties.
- Environmentally friendly product.
- Offers good adhesion.
- Ready to use without any additives.
- Strengthen the surface.

Properties	Results
Finish	Matt
Colour	Off White
Density at 25°C	Approx. 1.76 Kg / Ltr.
Solid Content by Volume (%)	52 ± 2
VOC – Volatile Organic Compound	10 (g/l) "according to EU Regulation"
Diluents /Thinner	Dilution is not required
Drying Time at 25°C and relative humidity 50%	• Touch Dry: 30 min • Recoat: 2 - 3 Hour •FullDry: 5 - 6 hours

PACKAGING

Refer to company price list or contact the local representative.

SAFETY PRECAUTIONS

- Please refer to material safety data sheet (MSDS) before using the product
- Please revert to technical office for application advice.
- For alternative systems may be specified, depending on area of use.

INSTRUCTIONS FOR USE

1. Surface preparation:

- Surface must be clean, free from oil, grease, dirt, chalk, loose paint and any other foreign materials.
- Old painted surfaces should be cleaned first from all loose paint and other contaminants that can affect adhesion
- Absorbent substrates should be moistened with water and sealed.
- Concrete, plaster and masonry surfaces should be fully cured before applying putty (at least 4 weeks for concrete and 10 days for plaster and masonry).

2. Recommended Application System:

- Use one of the suitable primers from SCIB for priming purposes and to seal porous surfaces.
- UNOSHIELD is applied with no further additions / dilution.
- Surface must be completely dry between successive coats (minimum 2 hours drying time depending on temperature and humidity)
- In case more than 5 mm layer thickness is required, it is advisable to apply in more than one layer with 24 hours interval (or less depending on temperature) between each layer. before use.
- First coat to be diluted with 10 15% water.
- Second coat to be diluted with 5 10% water.
- Wait 4 hours between each coat for complete drying.
- Substrate should be sanded lightly between two coats.
- Application of one of the suitable primers from SCIB after putty application helps to increase spreading and adhesion.

APPLICATION TOOLS



THEORETICAL COVERAGE

0.5 - 1 Kg /m² Practical coverage varies depending on surface porosity, application method, and losses.

STORAGE & SHELFLIFE

18 months in original tightly closed containers away from direct sunlight and excessive heat.

UNOSHIELD - Page 1 Of 1

Our recommendations are based on extensive research as well as practical experience. However, as the product is often used under conditions beyond our control, we cannot quarantee anything but the quality of the product itself. We reserve the right to change the given data without notice. Please note that this data sheet supersedes any previous prints. For any additional information, please consult our technical office.















اونوشيلد



معجون خارجي فائق الجودة

الوصف والاستخدامات

- أونوشيلد معجون فإئق الجودة شديد التحمل جاهز للإستخدام بأساس أكريليك كوبوليمر. -صمم خصيصا للإستخدام الخارجي ويصلح أيضا للإستخدام فى الظروف القاسية داخليا.
- قدرة ممتازة على ملئ الفجوات والثقوب مع سهولة في
 - منتج بأساس مائي وصديق للبيئة.
 - له قدرة عالية على الألتصاق.
 - جاهز للإستخدام بدون أضافات.
 - يعطى قوة للسطح.

خصائص المنتج		
النتيجة	الخصائص	
а	الشكل النهائي	
أوف وايت (شبه أبيض)	اللون	
تقریباً ۱٫۷٦ کجم / لتر	الكثافة عند درجة ٢٥ °م	
7 ± 07	النسبة المئوية للمواد الصلبة بالحجم ٪	
١٠ جرام/ لتر «طبقا للمواصفات الأوروبية»	المواد العضوية المتطايرة (VOC (g/Ltr.)	
جاهز للإستخدام بدون تخفيف	المذيب / المخفف	
• جفاف مبدئي : ٣٠ دقيقة • و جه ثاني : ٢ - ٣ ساعات • جفاف نهائي : ٥ - ٦ ساعات	زمن الجفاف عند درجة °۳۵ منوية ونسبة الرطوبة ۵۰ ٪	

العبوات المتوفرة

• لمزيد من المعلومات يرجى الرجوع إلى قائمة أسعار الشـركة أو أقرب وكيل.

تعليمات الأمن والسلامة

- يرجى الرجوع إلى نشرة السلامة الخاصة بالمنتج (MSDS) قبل الأستخدام.
 - يرجّى الرجوع إلى المكتب الفني لمزيد من الأستشارات بخصوص التطبيق.
 - يمكن توصيف أنظمة دهان بديلة وذلك بناء على مناطق الأستخدام.

تعليمات الاستخدام

١. تجهيز السطح :

- يراعى نظافة السطح المراد دهانه وخلوه من الزيوت والشحوم والأتربة كما يراعي تماسك السطح المراد دهانه وعدم تجييرة أو تبديره.
- في حالة تطبيق المنتج على أسطح مدهونة مسبقاً يراعى نظافة السطح وإزالة طبقة الدهانات غير المتماسكة وخلو السطح من أي مواد غريبة لضمان قوة الإلتصاق.
 - براعى معالجة الأسطح المسامية بإستخدام السيلر المناسب قبل تطبيق المعجون.
- -يراعي جفاف الأسطح الأسمنية والجبسية و المحارة قبل تطبيق المعجون (على الأقل ٤ اسابيع للخرسانة و ١٠ أيام للمحارة).

٢. خطوات التنفيذ المقترحة :

- یستخدم برایمر مناسب من برایمرات **سکیب** لغلق المسام قبل تطبيق المعجون.
- يتم تطبيق معجون أونوشيلد دون أي إضافات أو تخفيف.
 - يجب ترك زمن كافى للجفاف بين الطبقات المتتالية (ساعاتان على الأقل حسب درجة الحرارة و الرطوبة).
- في حالة عمل سمك من المعجون يزيد عن ٥ مم ينصح بعمل أكثر من طبقة مع فاصل زمني ٢٤ ساعة بين كل طبقة (يمكن أن تقل الفترة الزمنية حسب درجة الحرارة
- يراعى عمل صنفرة خفيفة لسطح المعجون قبل تطبيق الطبقات التالية.
- دهان طبقة **السيلر/البرايمر** المناسب من **سكيب** فوق المعجون وقبل الدهان تساعد على تحسين معدل الإستهلاك للدهانات و ألتصاقها بالسطح.

أدوات التطبيق



معدل الاستهلاك الاسترشادي

من ٥٠٠ - ١كجم/م التغطية الفعلية تختلف حسب حالة السطح و مسامية من السطح و طرق التنفيذ.

التخزين ومدة الصلاحية

١٨ شِهر في العبوة الأصلية محكمة الغلق و بعيدا عن أشعة الشمس المباشرة و الحرارة.

أونوشـيلد - صفحة 1 من 1 ان المعلومات الواردة فـى هـذه الصفحـة هـى افضل مـا لدينا من المعرفة القائمة على التجارب المعملية والخيرة العملية. وبما ان المنتج يسـتعمل غالبا تحت طروف خارج نطاق مرافيتنا، فاننا لا نسـتطيع ضمان أى شـئ سـوى نوعية المنتج نفسـه ونحتفظ بحق تغيير البيانات المعطاه دون اشـعار مسـبق. هذه المواصفات الفنية تلغى أى مواصفات سـابقا. لمزيد من الاستفسـار يرجى مراجعة المكتب الفنـي.









